

#### ПРЕДПРИЯТИЕ МАКСАЭРО

- Производство воздуховодов и систем вентиляции
- Клапаны противопожарные
- Клапаны дымоудаления
- Вентиляторы общепром, дымоудаления, крышные

220056, г. Минск, ул. Стариновская, 15

Тел./факс: +375 17 244-67-44, 258-67-51, 347-73-56, 252-54-27

Velcom: +375 29 603-88-99

E-mail: [olegaero@yandex.by](mailto:olegaero@yandex.by)

[www.maxaero.by](http://www.maxaero.by)



## Рукавные фильтры Donaldson Dura-Life (из полиэстера)



# Replacement Elements

## Media

---

| Dura-Life®                                                                                    |                                                                                                                                                                                                       |
|-----------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Appearance                                                                                    | White                                                                                                                                                                                                 |
| Use                                                                                           | Filter bags                                                                                                                                                                                           |
| Composition                                                                                   | 100% polyester                                                                                                                                                                                        |
| Area weight (DIN 53854)                                                                       | 340 g/m <sup>2</sup>                                                                                                                                                                                  |
| Thickness (DIN 53855)                                                                         | 1.6 mm                                                                                                                                                                                                |
| Air permeability (DIN 53887)                                                                  | 170 l/dm <sup>2</sup> min @ 200 Pa                                                                                                                                                                    |
| Dimensional stability @ 177°C                                                                 | <3.0%                                                                                                                                                                                                 |
| Surface finish                                                                                | None                                                                                                                                                                                                  |
| Additional treatments                                                                         | Heat set                                                                                                                                                                                              |
| Surface electrical resistance                                                                 | Not applicable                                                                                                                                                                                        |
| BIA category                                                                                  | Not applicable                                                                                                                                                                                        |
| Temperature (dry heat)<br>Continuous<br>Peaks                                                 | 135°C<br>150°C                                                                                                                                                                                        |
| Chemical resistance<br>Hydrolysis<br>Acids<br>Alkalis<br>Oxidising agents<br>Organic solvents | Poor<br>Good<br>Good<br>Very good<br>Very good                                                                                                                                                        |
| Abrasion resistance                                                                           | Very good                                                                                                                                                                                             |
| Supports combustion                                                                           | Yes                                                                                                                                                                                                   |
| Application field                                                                             | Dura-Life is suitable for the majority of temperature and chemical environments normally encountered in Dalamatric applications including acidic and weak alkaline conditions at ambient temperature. |